



Granite[®] Deep Mat 40 microns

Inspired by Nature



Properties

- Nice aesthetic appearance: matt and wrinkled
- Very good formability
- Very good corrosion resistance
- Thermosetting paint
- Surface treatment and paint: free of hexavalent chromium and heavy metals

Applications

External building and general industry applications: tiles, cladding etc

Description

Thickness ⁽¹⁾	40 microns
Composition	Front 15 microns primer + 25 microns top coat Back: 5, 7, 10 or 12 microns backing coat Double-side finish available
Gloss (Gardner 60°) ⁽¹⁾	Maximum 5 GU
Colours	Specific colour palette
Appearance	Wrinkled
Temporary protection (optional)	Strippable films are usually not suitable for wrinkled surfaces

Performance

Adhesion of the coating (T-bend)	≤ 1 T
Resistance to cracking on bending (T-bend)	≤ 2 T
Impact resistance	18 J
Resistance on deformed parts: Marciniak test	≤ 1C1
Clemen scratch resistance	≥ 1.5 kg
Corrosion resistance: • Salt spray test • Corrosion resistance category	500 hours RC4
Condensation resistance (QCT)	1500 hours
UV resistance: • QUV (UVA + H ₂ O) test (2000 hours) • UV resistance category	ΔE ≤ 3; GR ≥ 60% RUV3
Resistance to acids and bases	Good
Resistance to solvents: • Aliphatics and alcohols • Ketones • Aromatics	Very good Low Good to very good

Automatic guarantee

- Non-perforation of the sheet metal ≤ 20 years, depending on the external environment
- Non-delamination of the paint ≤ 20 years, depending on the external environment
- Aesthetic appearance (ΔE ≤ 3; Gloss retention ≥ 50%) ≤ 5 years, depending on the geographic location and the paint colour category

Remarks

These performance characteristics refer specifically to metallic coating Z225 (guaranteed minimum).
If any product (film, oil, foam, glue, paint etc) is to be applied after coil delivery, compatibility with the coating needs to be checked first.
Although we take great care to reproduce the same aesthetic aspect on each coil, ArcelorMittal cannot guarantee the visual consistency from one batch to another. Consequently, you need to consider placing one single order for one building; standard samples can only serve as a guide.

(1) Nominal value, tolerance according to EN 10169