

Backing coat 25 microns

Properties

- Robust backing coat
- Very good corrosion protection
- Colour consistency
- Compatible with foam
- Thermosetting paint
- Surface treatment and paint: free of hexavalent chromium and heavy metals

Applications

Reinforced backing coat, fitting for Granite® HD Xtreme, Granite® HDX and Granite® Storm

Description

Thickness ⁽¹⁾	25 microns
Gloss (Gardner 60°) ⁽¹⁾	30 GU
Colours	B 7032 & B 9002 Other colours on request

Performance

Adhesion of the coating (T-bend)	≤ 2 T
Flexibility of the coating	≤ 3 T
Clemen scratch resistance	1.5 kg
Salt spray test	500 hours
Condensation resistance:	
• QCT test	1500 hours
• Corrosion protection category	CPI4
Storage test (6 weeks wet pack test 50°C)	< 2S2
Foam adhesion	Needs to be checked by the end user with his specific products

Remarks

These performance characteristics refer specifically to metallic coating Z275 (guaranteed minimum).

(1) Nominal value, tolerance according to EN 10169